

Novact Corporation (Member of Allied Color Group)

		Product Name (C.I. #) Allifix	General Properties			Application Suitability			Light Fastness (AATCC 161-2000)		Crock Fastness (ISO 105-X12)		Washing Fastness (ISO 105-C06/014)		Other Wet Fastness		Perspiration Fastness (ISO 105-E04)	
1%	4%		Solubility (gpl) at 60°C	Substantivity	Dischargeability	Exhaust Dyeing	Cold Pad Batch Dye	Continuous Dyeing	1/1 S/D	1/6 S/D	Dry	Wet	Shade Change	CO (Staining)	Hypochlorite Bleach ISO 105-N01	Peroxide Bleach ISO 105-N02	Acidic	Alkaline
		Yellow SP4GL (Re. Yellow 160)	120	M	○	△	○	◇	5	4	4-5	4-5	4-5	5	1	4	4-5	4-5
		Yellow SP-3RF (Re. Yellow 145)	100	M	○	△	○	◇	5	5	5	5	4-5	5	1	3-4	4	4
		Orange SP-2R (Re. Orange 122)	100	H	◇	△	△	△	5	4	4-5	4	4	4	3	4	4-5	4-5
		Red SP-3B (Re. Red 195)	100	H	◇	△	△	△	5	5	4-5	4	4-5	4-5	1	4	5	5
		Red SP-6BL (Re. Red196/250)	80	H	◇	△	△	△	5	5	4	3-4	4	4	1	4	5	5
		Re. Red SP-RB (Re. Red 198)	100	H	◇	△	△	△	5	4	4-5	4	5	5	1	3	5	5
		Violet 5R (Re. Violet 5)	100	M	○	△	△	△	5	5	3-4	3	4-5	4	2	4	5	5
		Turquoise Blue SP-G (Re. Blue 21)	100	H	◇	△	△	△	5	5	3-4	3	3-4	3-4	3	4	4-5	4-5
		Brilliant Blue R (Re. Blue 19)	80	H	◇	△	△	△	5	4-5	4	3-4	4-5	4-5	3	4-5	4-5	5
		Blue HE-GN (Re. Blue 198)	100	M	△	△	○	◇	4	3	4-5	3-4	4-5	4-5	3	4	5	5
		Blue SP-BRF (Re. Blue 221)	120	H	△	△	△	△	5	4	4-5	4	4-5	4-5	3	3	4	4
		Navy Blue SPBF (Re. Blue 222)	100	H	△	△	△	△	4	3	4-5	4	4-5	4-5	1	3	5	5
		Black B (Re. Black 5)	100	VH	△	△	△	△	5	3-4	3	2-3	5	4	1	3-4	5	5
		Black ED (Re. Black Mix)	100	VH	△	△	△	△	5	4	4	3-4	4	4	4	4	5	5

Keys: △ = Recommended ○ = Partially Recommended ◇ = Not Recommended VH = Very High H = High M = Medium L = Low