
































Colour Sample 色樣	Allilon Disperse Dyes 中美 分散性染料	索弓號/C.I.NO.	染色深度/Dyeing Depth (o.w.f.%)	Applicability 應用性能				類別 / Classification	pH 範圍 / pH Range	Fastness / 牢度						
				低溫染色(導染) / Carrier	高溫染色 / H.T. Dyeing	熱熔 / Thermosol	印染 / HTS HPS Print			日晒 / Light Fastness	Washing 水洗		Rubbing 摩擦		昇華 / Sublimation	
											色變 / Color Change	污染 / Staining	乾式 / Dry	濕式 / Wet		
																5

● Supplementary Dyes (Eko-TEX Free) / 其它補充性染料 (環保型)

	Yellow 分散黃	C-5G C-5G	Y-119	1.0	△	◎	○	◎	C	4.6	6-7	5	5	4.5	4.5	4
	Yellow 分散黃	4G 4G	Y-211	1.0	△	◎	◎	◎	C	4.9	6-7	4.5	4.5	4.5	4.5	4
	Yellow 分散黃	SE-RF SE-RF	—	1.0	△	◎	◎	◎	C	4-10	6	5	4.5	5	5	5
	Gold Yellow R 分散金黃 R	R R	—	1.0	△	◎	◎	◎	C	4.8	6	4.5	4.5	4.5	4.5	4
	Orange 分散橙	2RFSN 2RFSN	—	1.0	○	◎	◎	◎	C	4.9	6	4.5	4	4.5	4.5	4
	Orange 分散橙	REL REL	0-61	1.0	○	◎	◎	◎	C	4.9	6	4.5	4	4.5	4.5	4
	Orange 分散橙	RGL RGL	—	1.0	○	◎	△	◎	C	4-10	5	4.5	4.5	5	5	4.5
	Orange 分散橙	3R-LS 3R-LS	—	1.0	○	◎	△	◎	C	4-10	6	4.5	4	4	4	4.5
	Orange 分散橙	H3R H3R	0-25	0.8	○	◎	△	◎	B	4-11	5-6	4	4	4.5	4.5	3
	Brown 分散棕	S-3RL S-3RL	—	2.5	—	◎	◎	◎	D	4.6	5	5	5	4.5	4.5	4.5
	Brown 分散棕	S-2BL S-2BL	—	2.0	—	◎	◎	◎	D	4.6	5	5	5	4.5	4.5	4.5
	Brown 分散棕	RSN RSN	—	2.0	—	◎	◎	◎	D	4.6	5	5	5	4.5	4.5	4.5
	Brown 分散棕	KPS KPS	—	2.0	△	◎	△	◎	C	4-9	5	5	5	4.5	4.5	4
	Brown 分散棕	3RN 3RN	Br-4	2.0	○	◎	△	◎	C	4.9	5-6	5	4	4.5	4.5	4
	Scarlet 分散大紅	2GH 2GH	R-50	1.0	○	◎	△	◎	B	4-11	5	4	4	4	4	3-4

Colour Sample 色樣	Allilon Disperse Dyes 中美分散性染料		索引號/C.I.NO.	Applicability 應用性能				類別 / Classification	pH 範圍 / pH Range	Fastness / 牢度						
				染色深度/Dyeing Depth (o.w.f.%)	低溫染色(導染)/Carrier	高溫染色/H.T Dyeing	熱熔/Thermosol			印染/HTS HPS Print	日晒/Light Fastness	Washing 水洗		Rubbing 摩擦		昇華 / Sublimation
												色變/Color Change	污染/Staining	乾式/Dry	濕式/Wet	
Scarlet 分散大紅	SLK SLK	R-135	1.5	—	◎	◎	◎	D	4-6	5	5	5	4.5	4.5	4-5	
Scarlet 分散大紅	GS GS	R-153	1.0	△	◎	◎	◎	C	4-9	5	4	4	4.5	4.5	4	
Scarlet 分散大紅	H4GFS H4GFS	—	2.0	△	◎	△	◎	C	4-9	5	4.5	4	4.5	4.5	4	
Scarlet 分散大紅	C-GFS C-GFS	—	2.0	△	◎	△	◎	C	4-9	5	4.5	4	4.5	4.5	4	
Red 分散紅	BS BS	R-152	1.5	△	◎	◎	◎	C	4-9	5-6	4	4	4.5	4.5	3-4	
Red 分散紅	RBLS RBLS	R-177	1.0	—	◎	◎	◎	D	4-6	5-6	5	4.5	4.5	4.5	4-5	
Pink 分散桃紅	S-FR S-FR	R-91	1.0	△	◎	◎	◎	C	4-9	7	5	4.5	5	5	4-5	
Red 分散紅	FTS FTS	R-343	0.5	—	◎	◎	◎	D	4-9	5-6	5	4.5	5	5	4	
Rubine 分散暗紅	FL FL	R-73	1.0	△	◎	○	◎	C	4-9	5-6	4.5	4.5	4.5	4.5	4	
Rubine 分散暗紅	B B	R-13	1.0	○	◎	△	—	B	4-11	4.5	4	4	4	4	3	
Rubine 分散暗紅	CBSF CBSF	V-33	1.0	△	◎	◎	◎	C	4-6	6-7	4.5	5	4.5	5	4-5	
Red Violet 分散紅紫	FBL FBL	V-26	1.5	○	◎	△	◎	B	4-9	6-7	4.5	4.5	4.5	5	4	
Violet 分散紫	S-3RL S-3RL	V-63	1.0	△	◎	○	◎	C	4-9	5	4.5	4.5	4.5	4.5	4	
Violet 分散紫	2RE 2RE	V-28	1.0	○	◎	○	◎	B	4-9	6	4.5	4.5	4.5	4.5	3-4	
Violet 分散紫	RL RL	V-28	0.5	○	◎	○	◎	B	4-9	6	4.5	4.5	4.5	4.5	3-4	
Navy Blue 分散藍	C4R C4R	V-93	1.0	△	◎	◎	◎	C	4-9	5	5	5	4.5	4.5	4	

Colour Sample 色樣	Allilon Disperse Dyes 中美 分散性染料		索引號/C.I.NO.	Applicability 應用性能				類別 / Classification	pH 範圍 / pH Range	Fastness / 牢度						
				染色深度/Dyeing Depth (o.w.f.%)	低溫染色(導染) / Carrier	高溫染色 / H.T. Dyeing	熱熔 / Thermosol			印染 / HTS HPS Print	日晒 / Light Fastness	Washing 水洗		Rubbing 摩擦		昇華 / Sublimation
												色變 / Color Change	污染 / Staining	乾式 / Dry	濕式 / Wet	
	Dk/Blue 分散暗藍	3RN 3RN	—	1.0	△	○	○	○	C	4-9	5	5	5	4-5	4-5	4
	Blue 分散藍	FBLN FBLN	—	1.0	△	○	○	○	C	4-9	5-6	5	5	5	5	4-5
	Blue 分散藍	BLS BLS	B-183-1	1.5	—	○	○	○	C	4-9	6	4-5	5	5	4-5	4-5
	Blue 分散藍	C-2R C-2R	B-183-1	1.5	—	○	○	○	C	4-9	6	4-5	5	5	4-5	4-5
	Blue 分散藍	S-2BLN S-2BLN	B-165	0.5	△	○	○	○	D	4-9	6	5	4-5	4-5	5	4-5
	Blue 分散藍	6G 6G	B-291	1.0	△	○	○	○	C	4-9	5	4-5	4	5	5	4
	Green 分散綠	C6B C6B	Gr-9	1.5	—	○	○	○	C	4-9	6-7	5	4-5	4-5	4-5	4
	Navy Blue 分散深藍	E/C E/C	B-79	1.0	—	○	○	○	D	4-6	6	5	4-5	4-5	4-5	4-5
	Navy Blue 分散深藍	C-SE C-SE	—	2.0	△	○	○	○	C	4-9	5	5	4-5	4-5	4-5	4
	Navy Blue 分散深藍	2RSE 2RSE	—	2.0	△	○	○	○	C	4-9	5	5	4-5	4-5	4-5	4
	Gray 分散灰	GL-S GL-S	—	1.0	○	○	○	○	B	4-9	6	5	5	5	5	4-5
	Black 分散黑	GI GI	—	3.0	—	○	○	○	D	4-6	5-6	5	4-5	4-5	4-5	4-5
	Black 分散黑	KSL KSL	—	3.0	—	○	○	○	D	4-6	5-6	5	4-5	4-5	4-5	4-5
	Black 分散黑	HGFS HGFS	—	2.5	—	○	○	○	D	4-6	6	5	4-5	4-5	4-5	4-5
	Black 分散黑	2BSF 2BSF	—	2.5	—	○	○	○	D	4-6	6	5	4-5	4-5	4-5	4-5
	Black 分散黑	C-SE C-SE	—	2.5	△	○	○	○	C	4-9	5	5	4-5	4-5	4-5	4